Searching PAJ Page 1 of 2

PATENT ABSTRACTS OF JAPAN

(11)Publication number: 09-107195(43)Date of publication of application: 22.04.1997

(51)Int.Cl.

H05K 9/00 B32B 7/02 B32B 27/00

(21)Application number : 08-198051

(22)Date of filing:

26.07.1996

(71)Applicant : HIRAOKA & CO LTD

(72)Inventor: OBAYASHI TSUTOMU

SUZUKI HIROSHI

(30)Priority

Priority number: 02147299 Priority date: 07.06.1990 Priority country: JP


(54) MANUFACTURE OF HIGH ELECTROMAGNETIC WAVE SHIELDING COMPOSITE SHEET

(57)Abstract:

PROBLEM TO BE SOLVED: To integrate a conductive fiber material with a resin matrix layer in the layer at a desired position without breaking the conductive fiber material, by depressurizing a deposited layer of conductive short fiber and a resin matrix film layer, and forming a conductive fiber-resin integrated layer.

SOLUTION: A resin matrix layer is formed by applying a resin film containing polymer material as a main component on to a sheetlike base substance 1. In at least one surface-side surface layer part of a resin matrix layer formed on this sheetlike base substance 1, a deposited laminar substance of a specified quantity of conductive short fiber is buried, and a conductive fiber-

resin integrated layer 2 is formed by it. In the formation



of the conductive fiber-resin integrated layer like this, conductive short fiber is distributed with a high density only in the surface layer part of at least one surface of the resin matrix layer, forming a deposited laminar substance. It does not matter if conductive short fiber is not

Searching PAJ Page 2 of 2

distributed in the remaining part of the resin matrix layer partically, or is distributed with a high density practically over the whole volume.